A new dynamic-XPS end-station for beamline P04 at PETRA III/DESY

Sergey V. Babenkov^{a,*}, Victor Y. Aristov^{b,c}, Olga V. Molodtsova^a, Leif Glaser^a, Ivan Shevchuk^a, Frank Scholz^a, Jörn Seltmann^a, and Jens Viehhaus^a

^a*Deutsches Elektronen-Synchrotron DESY, Notkestraße 85, 22607 Hamburg, Germany*

^b*Institute of Solid State Physics of Russian Academy of Sciences, Chernogolovka 142432, Russia*

^c*Institut für Theoretische Physik, Universität Hamburg, Jungiusstraße 9, D-20355 Hamburg, Germany*

Abstract

We report on a new dynamic-XPS end-station for real-time investigations of advanced materials. The end-station is based on a new Argus hemispherical electron spectrometer with high speed detection system. In combination with the high brilliance XUV beamline P04 at PETRA III it provides users at PETRA III a unique tool for fast (down to 0.1 sec/spectrum) and detailed investigations compared to existing XPS devices at other beamlines.

Keywords: Electron spectrometer; Dynamic-XPS; Snapshot; High resolution.

1. Introduction

Photoelectron spectroscopy is a well established and commonly used technique to obtain information about electronic structure of surface of solid state materials and rare gases [1]. Technical progress in construction of X-ray sources
5 as well as in manufacture of electron spectrometers and detectors provides researchers a possibilities to investigate more complex and advanced materials. For instance, growth processes of graphene on several substrates [2–5], metal-organic interfaces formation [6, 7], fabrication of hybrid organic-inorganic systems [8, 9] and etc. From the other hand, the synthesis of such materials may

*Principal corresponding author

Email address: `sergey.babenkov@desy.de` (Sergey V. Babenkov)

10 occasionally involve fast processes, e.g. reaction kinetics [10–12], which consequently should be precisely controlled and characterised. The problem could be solved by measuring dynamic photoelectron spectra with acquisition times per spectrum in the millisecond time resolution [11].

One way to realise experiments with sufficient time resolution is the combination of a high brightness beamline with a new hemispherical analyser Argus
15 (Omicron NanoTechnology GMBH, Germany). This analyser uses a 128 channel multi-anode detector, which can generate photoelectron spectra in both traditional scanning as well as a so-called snapshot mode (128 channels of the electron detector covered the whole core level peak). The snapshot mode allows
20 dynamic data acquisition in the millisecond regime. The analyser energy resolution (30 meV at 250 eV kinetic energy) is in line with the beamline specifications and allows sufficient resolution for any high resolution time dependent XPS experiments. The described end-station is designed, built up and installed into the beamline P04 (PETRA III, DESY, Hamburg). Initial experiments success-
25 fully demonstrated the potential of obtaining dynamic photoelectron spectra at P04 for *in-situ* growth studies, which could be applied to other research fields [13, 14].

2. Design of experimental station

2.1. Overview of instrument

30 The experimental station consists of 3 main parts (Fig. 1). The middle one is a small ultra-high vacuum (UHV) analysis chamber (base pressure below 1×10^{-10} mbar) equipped with the hemispherical electron-analyser, which is connected on the right side of the analysis chamber (Fig. 1). The analysis chamber includes a manipulator with 4 degrees of freedom (x , y , z directions and polar
35 angle around the z axis). The main part of manipulator is a special designed head, whose design is described below (see sec.2.3). The analysis chamber is also equipped with a quartz microbalance, an effusive capillary gas source and an evaporator of metals. The metal evaporator and an effusive capillary gas

source are placed within small angle with respect to photon beam (12.5°). This
 40 arrangement allows to perform *in-situ* deposition of metal and apply gas at-
 mosphere in the vicinity of sample surface, with only barely increases the base
 pressure during measurements. Furthermore, CF-40 flanges allow to mount
 additional devices.

To the left side of [Figure 1](#) UHV preparation chamber (base pressure below
 45 1×10^{-10} mbar) is attached to the analysis chamber. This chamber is equipped
 with a quartz microbalance, a sputtering gun, an organic evaporator and a linear
 manipulator with propose-built sample transfer system. In addition, there is a
 sample garage for a number of holders and a gas inlet system as well as a fast
 entry lock window which provides the possibility of fast introduction of new
 50 samples, if required. Design of sample holder (for details see [sec.2.3](#)) provides
 possibility to control sample temperatures in the range from 300 up to 1700 K
 during preparation procedure.

2.2. The hemispherical electron analyser.

Dynamic XPS experiments aim for monitoring of time depended processes
 55 e.g. the temperature stimulated Graphene growth on the surface of cubic-
 SiC/Si. Specifically, in order to observe irreversible processes with sufficient
 time resolution and data quality high photon flux and multi bunch mode from
 the synchrotron source, optimized spectrometer transmission and an adequate

Figure 1: Experimental setup: (from left to right) sample preparation chamber, analysis chamber, spectrometer Argus.

Figure 2: Detector scheme: each electron impact starts a cascade of electrons propagating through the MCP stack. The amplified electron signals are collected by a stripe anode array which is connected to 128 dedicated amplifiers and counters are situated in UHV closely connected to the stripe anode for optimum signal to noise ratio.

detection system are essential for such experiment.

60 Other time resolved experiments [15] demand for sophisticated experimental setups which allow ultra fast time resolution into the fsec regime. Another commonly used approach is a pump-probe setup which utilizes synchronized data acquisition with the pump and probe light pulses. A key advantage of such experiments is the repeatability of the process which allows accumulating
65 signals over multiple repeats and as result moderate duty cycles can be accepted [16].

In the presented dynamic XPS end station design a modern high transmission turnkey hemispherical electron spectrometer system (Argus) with small spot lens for XPS, imaging XPS and AES applications has been implemented.
70 It is based on an electrostatic hemispherical energy analyser with a mean radius of 124 mm. The analyser focuses electrons in both angular directions, from the entrance onto the exit plane.

Key to the experimental setup is a new type of multianode detector [17] which uses a microchannel plate (MCP) to amplify the electron signals (Fig. 2).
75 However in contrast to other multi channel detectors [18] the amplified signals impact on an on-chip stripe-anode array which is hardwired to 128 independent

working pulse counters all implemented in UHV allowing for massive parallel detection. Compared to other detection concepts the proximity of anode and pulse counting electronics in UHV is highly optimized. As a result the sensitivity and the signal to noise performance of the detector are excellent.

The detector has demonstrated quantitative XPS results with peak count rates larger than 100 Mcps [17]. Special care has been taken to calibrate the detector in order to allow quantitative snapshot XPS performance. The detector has been tested in snapshot mode signature free up to the highest count rates.

For time resolved experiments the detector allows continuous run in snapshot mode with dwell times in the msec time regime. The analyser is operated by MATRIX Automated Task Environment (MATE) software (for details see Ref[23]).

2.3. Manipulator head of sample holders and sample transfer system

The design of sample holder, manipulator head and sample transfer system is based on ASPHERE III Setup sample holder system (University of Kiel) [19, 20]. The stainless steel manipulator head has 3 slots for sample holders and is connected directly to manipulator rod (Figure 3). The rotation axis of manipulator coincides with sample surface, thereby it allows it to rotate a

Figure 3: Current view of analysis chamber. The sample holder with heated piece of SiC/Si wafer (around 800° C), the gas source in front of sample surface, as well as the electron analyser entrance aperture and metal evaporator can be seen.

Table 1: Parameters of Soft X-Ray beamlines with end stations based on delay-line detection system.

Beamline	Photon energy range eV	Resolving power	Photon flux photons/s@RP	Spot size $\mu\text{m} \times \mu\text{m}$	Polarization
XUV P04, DESY Expected in 2015	250 - 3000 50 - 3000	$3 \times 10^4 @ 300 \text{ eV}$	$5 \times 10^{12} @ 1 \times 10^4$	Vertical $10 \mu\text{m}$ Horizontal $10 \mu\text{m}$	Circular Linear
SuperESCA, Elettra Tempo, Soleil	90 - 1800 50 - 1500	$3 \times 10^4 @ 400 \text{ eV}$ $5 \times 10^3 @ 400 \text{ eV}$	$1 \times 10^{11} @ 1 \times 10^4$ $4 \times 10^{12} @ 5 \times 10^3$	10×100 10×40	Circular, linear Circular, linear

sample without lateral shift. The upper slot is equipped with direct current heating and LN_2 cooling stages that allow to control the sample temperature in the range from 100 up to 1700 K. The contact sheets are arranged in a way that allows spectra acquisition in a wide range of the electron emission angles ($0 - 77.5^\circ$) while temperature changing. At the same time, 2 additional slots provide possibility to investigate samples at room temperature.

Figure 3 represents the current view of manipulator head and sample holder with heated piece of SiC/Si wafer. In addition, the position of capillary gas source, analyser and metal evaporator is indicated.

2.4. Key parameters of the setup

The experimental station is installed into Variable Polarization XUV beamline P04 at PETRA III. Table 1 presents of most important parameters of the beamline P04 and others, which are also using delay-line detection system [11, 21, 22]. Photon energy range of beamline P04 is 250 - 3000 eV. Optical mode, which makes use of the off axis radiation of the undulator, gives a potential to expand this range down to 50 eV. Resolving power (RP) is more than 10^4 ($> 3 \times 10^4 @ 300 \text{ eV}$). Photon flux is 5×10^{12} photons/s at resolving power 10^4 . Variable polarisation in 2013/14 is only between left- and right-handle circularly polarized. Spot size at sample is down to $10 \mu\text{m}$ (2013/14 in the vertical only). This combination of parameters makes the beamline most suitable for dynamic-XPS experiments, in comparison with other soft X-Ray beamlines.

Figure 4: Experimental spectrum of Xe 5p measured at 265 eV photon energy. Blue dots are experimental data. Red line is decomposition result of experimental data.

The energy resolution of the spectrometer was confirmed to be smaller than 30 meV for kinetic energies of about 250 eV using a Xenon gas phase target and the Xe 5p electron lines (Fig. 4). Similar value (25 meV) was estimated from Au 4f core level deconvolution.

120 The experimental spectra were recorded in snapshot mode (See sec. 3). Apart from scanning and snapshot modes, the design of spectrometer provides a possibility to scan a sample surface in XPS range without mechanical shift of the sample ("dynamic mode" of XPS). This mode allows to understand complex local chemistry and to obtain local PE spectra along the surface of analysed
125 sample with lateral resolution better than 60 μm [23, 24].

3. Time resolved *in-situ* observation of temperature stimulated graphene growth onto the surface of cubic-SiC/Si

Following our recent work [5, 25–27] the key attention was paid to investigation of graphene. The temperature stimulated self-organised growth of carbon
130 atoms into graphene structure is well studied on different substrates and by different methods [5, 25–32]. The methods are very laborious and consist of several steps (sublimation of Si, surface reconstruction of carbon, hybridisation of carbon-carbon bonds, etc) which should be successively tracked during preparation procedure [25]. There are different parameters (heating time of sample,

Figure 5: (a-f) Time evolution of C 1s core level snapshot PE spectra recorded during heating process. More than 900 snapshot spectra have been recorded with acquisition time of 1 sec/spectrum. A one of single snapshot spectrum at critical stages is shown. (g) Temperature of sample during the measurements.

135 applying surrounding atmosphere, heating temperature, etc) which could be changed during preparation procedure [25, 33]. There are no experiments with direct observation of real time preparation graphene layers and no methods to control an amount of graphene layers during preparation procedure.

Taken this into account, we followed for temperature stimulated process of
 140 *in-situ* graphene synthesis on piece of cubic-SiC/Si wafer by measuring of C 1s photoemission spectra in snapshot mode. The sample was annealed at 600-700° C during 1 hour to outgas the surface. Also the sample was flashed at 1100° C to remove silicon oxide from the surface. During the measurements we applied a direct current to sample to heat it up to 1350° C (Fig. 5(g)).
 145 More than 900 spectra of C 1s core level with acquisition time 1 sec/spectrum

were recorded during 15 minutes, using 750 eV photon energy and 70 eV pass energy (Fig. 5(a)-(e)). A one of single snapshot spectrum at critical stages is shown. Despite of quite high sample temperature and photon energy, as well as short time of spectrum acquisition, the spectra are well pronounced and allow
150 to observe the shape and ratio of peak during the preparation procedure. Due to current applied to the sample, the acquired spectra were shifted. In order to compensate this, the C 1s SiC peak was used as a reference.

At the first stage (Fig. 5(a)) of preparation procedure one can see a strong peak which corresponds to carbon in SiC bulk. Increasing the temperature (Fig.
155 5(b)-(e)) gives rise to a small additional component of the C 1s line shifted by 1.55 eV to higher binding energy. At the same time the bulk component is decreasing. This corresponds to a process of sublimation of Si atoms and a graphitisation of the surface [25]. Finally, at the last stage of preparation procedure (Fig. 5(f)), the temperature of sample has reached 1350° C. At this
160 temperature the carbon-carbon bonds undergo a reconstruction to sp² hybridisation which correspond to graphene formation [25]. After this procedure we *ex-situ* have moved our sample to another experimental station for LEED measurements, which proved the existence of a synthesised graphene layers on the SiC/Si wafer [25, 32].

165 4. Summary

The new dynamic-XPS end station is installed into beamline P04 (PETRA III, DESY), commissioned and available for regular users. The combination of beam line and end station allows to measure XPS spectra as a function of varying conditions, using both scanning and snapshot modes, with possibility to parallel
170 snapshot measurements of several core levels. Consequently, it opens access to real time investigations of fast flow processes and quantitative analysis of surface layers. For instance, one can follow the reaction kinetics by observation of spectrum shape or control of the deposition rate and amount of a given substance by monitoring the intensity or ratio of peaks in the snapshot spectra. Since

175 the beamline has possibility to smoothly change a photon energy, a NEXAFS
technique is available. Moreover, the beamline has several polarisation mode
and consequently there is a possibility to measure XMCD.

The shown results proof effectivity of the dynamic-XPS end station and the
ability to identify critical phases of fast real-time processes by following the
180 evolution of photoemission core level spectra.

To our knowledge there is no alternative beamline – end station combination
in terms of spectrum acquisition speed, photon flux, photon energy range and
photon energy resolution. The beamline parameters (linear polarisation mode,
beam focusing in horizontal plane, extension of photon energy range down to
185 50 eV) and new possibilities of end station (interconnection with beamline and
speed of the detection system) will be available very soon.

Acknowledgments

We want to thank Omicron NanoTechnology GMBH for providing the Argus
analyser, especially Konrad Winkler and Georg Prümper for support, as well
190 as Wolfgang Drube for the loan of equipment. We acknowledge support by the
P04 team and also all DESY-FS service groups and workshops. Moreover, we
thank the ASPHERE III collaboration, especially Arndt Quer, Erik Kröger,
Matthias Kalläne, Lutz Kipp (University of Kiel) as well as Hendrik Bentmann
and Cristoph Seibel (University of Würzburg) for valuable advice concerning
195 the design of the experimental stations and discussion of the results.

This work was supported by RFBR grants №13-02-00818, №14-02-00949 and
the BMBF-Project №05K12GU2, PSP-Element №U4606BMB1211.

References

- [1] J. F. Watts, J. Wolstenholme, An Introduction to Surface Analysis by XPS
200 and AES, 2014.

- [2] K. S. Kim, Y. Zhao, H. Jang, S. Y. Lee, J. M. Kim, K. S. Kim, J.-H. Ahn, P. Kim, J.-Y. Choi, B. H. Hong, Nature 457 (2009) 706. [doi:10.1038/nature07719](https://doi.org/10.1038/nature07719).
- [3] A. Reina, X. Jia, J. Ho, D. Nezich, H. Son, V. Bulovic, M. S. Dresselhaus, J. Kong, Nano Letters 9 (2009) 30. [doi:10.1021/nl801827v](https://doi.org/10.1021/nl801827v).
- [4] C. Berger, Z. Song, X. Li, X. Wu, N. Brown, C. Naud, D. Mayou, T. Li, J. Hass, A. N. Marchenkov, E. H. Conrad, P. N. First, W. A. de Heer, Science 312 (2006) 1191. [doi:10.1126/science.1125925](https://doi.org/10.1126/science.1125925).
- [5] V. Y. Aristov, G. Urbanik, K. Kummer, D. V. Vyalikh, O. V. Molodtsova, A. B. Preobrajenski, A. A. Zakharov, C. Hess, T. Hänke, B. Buchner, I. Vobornik, J. Fujii, G. Panaccione, Y. A. Ossipyan, M. Knupfer, Nano Letters 10 (3) (2010) 992. [doi:10.1021/nl904115h](https://doi.org/10.1021/nl904115h).
- [6] M. Cinchetti, K. Heimer, J.-P. Wüstenberg, O. Andreyev, M. Bauer, S. Lach, C. Ziegler, Y. Gao, M. Aeschlimann, Nature Materials 8 (2009) 115. [doi:10.1038/nmat2334](https://doi.org/10.1038/nmat2334).
- [7] V. Aristov, O. Molodtsova, Y. Ossipyan, B. Doyle, S. Nannarone, M. Knupfer, Organic Electronics 10 (2009) 8. [doi:10.1016/j.orgel.2008.09.001](https://doi.org/10.1016/j.orgel.2008.09.001).
- [8] J. C. Scott, Science 304 (2004) 62. [doi:10.1126/science.1095520](https://doi.org/10.1126/science.1095520).
- [9] V. Y. Aristov, O. V. Molodtsova, C. Laubschat, V. M. Zhilin, I. M. Aristova, V. V. Kveder, M. Knupfer, Applied Physics Letters 97 (2010) -. [doi:10.1063/1.3488809](https://doi.org/10.1063/1.3488809).
- [10] R. Balog, M. Andersen, B. Jørgensen, Z. Sljivancanin, B. Hammer, A. Baraldi, R. Larciprete, P. Hofmann, L. Hornekær, S. Lizzit, ACS Nano 7 (5) (2013) 3823. [doi:10.1021/nm400780x](https://doi.org/10.1021/nm400780x).
- [11] A. Baraldi, G. Comelli, S. Lizzit, M. Kiskinova, G. Paolucci, Surface Science Reports 49 (2003) 169. [doi:10.1016/S0167-5729\(03\)00013-X](https://doi.org/10.1016/S0167-5729(03)00013-X).

- [12] G. Ertl, *Angewandte Chemie International Edition* 47 (2008) 3524. doi:
10.1002/anie.200800480.
- 230 [13] C. Kunze, D. Music, M. to Baben, J. M. Schneider, G. Grundmeier, *Applied
Surface Science* 290 (2014) 504 – 508. doi:10.1016/j.apsusc.2013.11.
091.
- [14] S. McDonnell, B. Brennan, E. Bursa, R. M. Wallace, K. Winkler, P. Bau-
mann, *Journal of Vacuum Science Technology B* 32. doi:10.1116/1.
235 4878940.
- [15] S. Yamamoto, I. Matsuda, *Journal of the Physical Society of Japan* 82
(2013) 021003. doi:10.7566/JPSJ.82.021003.
- [16] W. Widdra, D. Bröcker, T. Gießel, I. Hertel, W. Krüger, A. Liero, F. Noack,
V. Petrov, D. Pop, P. Schmidt, R. Weber, I. Will, B. Winter, *Surface*
240 *Science* 543 (2003) 87. doi:10.1016/j.susc.2003.07.005.
- [17] P. Baumann, B. Krömker, G. Prümper, K. Winkler, R. Oiwa, J. Lenz,
M. Maier, A. Feltz, conference proceedings, ALC 2011.
- [18] A. Nambu, J.-M. Bussat, M. West, B. Sell, M. Watanabe, A. Kay, N. Man-
nella, B. Ludewigt, M. Press, B. Turko, G. Meddeler, G. Zizka, H. Spieler,
245 H. van der Lippe, P. Denes, T. Ohta, Z. Hussain, C. Fadley, *Journal
of Electron Spectroscopy and Related Phenomena* 137140 (2004) 691.
doi:10.1016/j.elspec.2004.02.156.
- [19] L. Kipp, Ph.D. thesis, Institut for Experimental and Applied Physics, Uni-
versity of Kiel (1992).
- 250 [20] E. Ludwig, H. Naggert, M. Kalläne, S. Rohlf, E. Kröger, A. Bannwarth,
A. Quer, K. Rossnagel, L. Kipp, F. Tuzek, *Angewandte Chemie (Interna-
tional Edition)* 53 (2014) 3019. doi:10.1002/anie.201307968.
- [21] J. Viehhaus, F. Scholz, S. Deinert, L. Glaser, M. Ilchen, J. Seltmann, P. Wal-
ter, F. Siewert, *Nuclear Instruments & Methods in Physics Research A* 710
255 (2013) 151. doi:10.1016/j.nima.2012.10.110.

- [22] F. Polack, M. Silly, C. Chauvet, B. Lagarde, N. Bergeard, M. Izquierdo, O. Chubar, D. Krizmancic, M. Ribbens, J.-P. Duval, C. Basset, S. Kubsy, F. Sirotti, AIP Conference Proceedings 1234 (2010) 185. [doi:10.1063/1.3463169](https://doi.org/10.1063/1.3463169).
- 260 [23] <http://www.omicron.de/en/products/334/1054/>.
- [24] U. Vohrer, C. Blomfield, S. Page, A. Roberts, Applied Surface Science 252 (2005) 61. [doi:10.1016/j.apsusc.2005.01.114](https://doi.org/10.1016/j.apsusc.2005.01.114).
- [25] A. N. Chaika, O. V. Molodtsova, A. A. Zakharov, D. Marchenko, J. Sánchez-Barriga, A. Varykhalov, I. V. Shvets, V. Y. Aristov, Nano Re-
265 search 6 (2013) 562. [doi:10.1007/s12274-013-0331-9](https://doi.org/10.1007/s12274-013-0331-9).
- [26] A. N. Chaika, O. V. Molodtsova, A. A. Zakharov, D. Marchenko, J. Sánchez-Barriga, A. Varykhalov, S. V. Babenkov, M. Portail, M. Zielinski, B. E. Murphy, S. A. Krasnikov, O. Lübben, I. V. Shvets, V. Y. Aristov, Nanotechnology 25 (2014) 135605. [doi:10.1088/0957-4484/25/13/135605](https://doi.org/10.1088/0957-4484/25/13/135605).
270
- [27] A. N. Chaika, N. N. Orlova, V. N. Semenov, E. Y. Postnova, S. A. Krasnikov, M. G. Lazarev, S. V. Chekmazov, V. Y. Aristov, V. G. Glebovsky, S. I. Bozhko, I. V. Shvets, Sci. Rep. 4 (2014) 3742. [doi:10.1038/srep03742](https://doi.org/10.1038/srep03742).
- 275 [28] A. Grüneis, D. V. Vyalikh, Phys. Rev. B 77 (2008) 193401. [doi:10.1103/PhysRevB.77.193401](https://doi.org/10.1103/PhysRevB.77.193401).
- [29] E. Rollings, G.-H. Gweon, S. Zhou, B. Mun, J. McChesney, B. Hussain, A. Fedorov, P. First, W. de Heer, A. Lanzara, Journal of Physics and Chemistry of Solids 67 (2006) 2172. [doi:10.1016/j.jpcs.2006.05.010](https://doi.org/10.1016/j.jpcs.2006.05.010).
- 280 [30] J. Hass, R. Feng, T. Li, X. Li, Z. Zong, W. A. de Heer, P. N. First, E. H. Conrad, C. A. Jeffrey, C. Berger, Applied Physics Letters 89 (2006) 143106. [doi:10.1063/1.2358299](https://doi.org/10.1063/1.2358299).

- [31] C. Virojanadara, R. Yakimova, J. Osiecki, M. Syväjärvi, R. Uhrberg, L. Johansson, A. Zakharov, Surface Science 603 (2009) L87. [doi:10.1016/j.susc.2009.05.005](https://doi.org/10.1016/j.susc.2009.05.005).
285
- [32] A. Ouerghi, M. Ridene, A. Balan, R. Belkhou, A. Barbier, N. Gogneau, M. Portail, A. Michon, S. Latil, P. Jegou, A. Shukla, Phys. Rev. B 83 (2011) 205429. [doi:10.1103/PhysRevB.83.205429](https://doi.org/10.1103/PhysRevB.83.205429).
- [33] K. V. Emtsev, A. Bostwick, K. Horn, J. Jobst, G. L. Kellogg, L. Ley, J. L. McChesney, T. Ohta, S. A. Reshanov, J. Röhl, E. Rotenberg, A. K. Schmid, D. Waldmann, H. B. Weber, T. Seyller, Nature 460 (2009) 203. [doi:10.1038/nmat2382](https://doi.org/10.1038/nmat2382).
290