

Real-time swelling-deswelling kinetics of nanogels driven by XFEL pulses

Francesco Dallari,^{1,2*} Irina Lokteva,^{1,3} Johannes Möller,⁴ Wojciech Roseker,¹ Claudia Goy,¹ Fabian Westermeier,¹ Ulrike Boesenberg,⁴ Jörg Hallmann,⁴ Angel Rodriguez-Fernandez,⁴ Markus Scholz,⁴ Roman Shayduk,⁴ Anders Madsen,⁴ Gerhard Grübel,^{1,3,4} and Felix Lehmkuhler^{1,3*}

¹Deutsches Elektronen-Synchrotron DESY, Notkestr. 85, 22607 Hamburg, Germany.

² University of Padua, Department of Physics and Astronomy, Via Marzolo 8, Padova, Italy

³ The Hamburg Centre for Ultrafast Imaging, Luruper Chaussee 149, 22761 Hamburg, Germany

⁴ European X-Ray Free-Electron Laser Facility, Holzkoppel 4, 22869 Schenefeld, Germany

*To whom correspondence should be addressed;

E-mail: francesco.dallari@unipd.it; felix.lehmkuehler@desy.de.

Stimuli-responsive polymers are an important class of materials with many applications in nanotechnology and drug delivery. The most prominent one is poly-N-isopropylacrylamide (PNIPAm). The characterization of the kinetics of its change after a temperature jump is still a lively research topic, especially at nm-length scales where it is not possible to rely on conventional microscopic techniques. Here we measured in real-time the collapse of a PNIPAm shell on silica nanoparticles with MHz X-ray photon correlation spectroscopy (XPCS) at the European XFEL. We characterize the changes of the particles diffusion constant as a function of time and consequently local temperature on sub- μ s time scales. We developed a phenomenological model to describe the observed data and extract the characteristic times associated to the swelling and collapse processes. Different from previous studies tracking the turbidity of PNIPAm dispersions and using laser heating, we find deswelling times below μ s time scales and two to three orders of magnitude slower swelling times.

1 Introduction

Stimuli-responsive hydrogels are a class of materials that undergo a volume phase transition as a response to variations in their local environment, such as changes in pH, pressure or temperature, enabling a wide range of applications from nanorobotics to drug delivery or adaptive optics (1–3). Collapse-inducing stimuli weaken the polymer-solvent interactions and strengthen the polymer-polymer ones, leading to a partial expulsion of the solvent from the gel. Many micro- and nano-gels are based on poly-N-isopropylacrylamide (PNIPAm) in water. While the equilibrium response of such systems has been intensively investigated (1, 4–6), it is only in recent years that the kinetics of the collapse mechanisms have been studied in time-resolved experiments providing new information on the details of these processes (7, 8). For PNIPAm, the collapse and swelling can be triggered by different stimuli: it can be induced by temperature (7, 9–13), cononsolvency effects (8, 14), and pressure (15–18). The knowledge of the timescales for this volume phase transition is very important for potential applications, especially for microgels, i.e., systems approaching the micro- or nanometer length-scales. For hydrogel particles with radii in the mm to μm range the swelling-deswelling kinetics is reasonably well described by the Tanaka model (19, 20) which predicts a characteristic time τ_c proportional to the square of the radius of a fully swollen particle. This sort of experiment is usually performed by inducing a temperature jump of the system and following the time evolution of a certain observable, e.g. optical density (13) or absorption spectrum (7, 12). In particular, if the energy is delivered first to the solvent, as, e.g. in the capacitor-discharges of Ref. (13), the microgel undergoes a two-step collapse which is attributed to the formation of an outer layer of collapsed polymer which slows down the escape of the water molecules trapped inside. Conversely, if the particles are heated directly, e.g., using Au-core-PNIPAm-shell systems as in (12) and a pump laser tuned to the plasmonic resonance of the core particle, a single step process is observed. Interestingly, the latter process shows markedly faster collapsing and swelling times (7).

Here we perform a direct measurement of the hydrodynamic radius of silica-PNIPAm core-shell particles dispersed in water. We apply MHz X-ray photon correlation spectroscopy (XPCS) using the X-ray pulse trains of European XFEL (EuXFEL) to measure the diffusion properties of the dispersion. Nanoparticles dispersed in liquids undergo Brownian motion with a diffusion constant (D) determined by the Stokes-Einstein relation via

$$D = \frac{k_B T}{6\pi R \eta(T)}, \quad (1)$$

where k_B is Boltzmann’s constant, T is the temperature, $\eta(T)$ the temperature-dependent viscosity and R the particle’s hydrodynamic radius, which for PNIPAm is also a function of temperature. Measuring the diffusion constant is therefore an effective way to track the swelling or deswelling of the polymers, as commonly done in Dynamic Light Scattering (DLS) experiments (1, 4, 5). XPCS is the X-ray analogue to DLS (21). Thanks to the shorter wavelengths, XPCS enables studies at much larger wave vector transfers covering simultaneously length

55 scales spanning from μm to nm in Small Angle X-ray Scattering (SAXS) configuration. In particular, it has been recently applied to study the phase behaviour of PNIPAm systems (22–24). The development of X-ray Free Electron Lasers (XFEL) with repetition rates in the MHz regime enabled the study of sub- μs processes (25–27). This is for instance the natural diffusion time scale of nanometer-sized particles dispersed in water.

60 Furthermore, XPCS at the European XFEL allows following the time evolution of driven and out-of-equilibrium systems over time and length-scales that cannot be reached with other more conventional experiments. In this scheme the ultrashort X-ray pulses act both as pumps heating the sample and as probes of the dynamics with sub- μs time resolution. Here, we present results from X-ray heating induced collapse and swelling of the PNIPAm shell at different
65 cross-linker concentrations and different shell thickness. An increasing number of research focusses on real-time dynamics of biological systems at FEL facilities (27, 28). FELs make possible to have a direct and real-time view on phenomena such as protein folding kinetics or phase separation, but at the same time pose important challenges in the form of radiation-induced effects and, most importantly, sample damage. Therefore, it is crucial to understand
70 the response of soft and biological matter under such intense and energetic photons on μs time scales. Depending on the softness of the particles, the X-ray pulse fluence and repetition rate, we observe different dynamical domains corresponding to swollen particles, collapsed particles as well as silica cores with radiation-induced loss of the PNIPAm shell. We find two time scales governing the dynamics of PNIPAm. A fast deswelling time in the range of 100 ns and a slow
75 swelling time of $\tau_s > 100 \mu\text{s}$. Compared to previous studies focusing on indirect quantities such as optical density we obtain a more direct measurement of the (de-)swelling process by accessing their diffusion properties on intrinsic microscopic length scales.

2 Results

The samples were probed by trains of 9 keV X-ray pulses with repetition rates of up to 2.24
80 MHz, see methods for details. Due to the high repetition rate of intense X-ray pulses, the samples experience sequential heating. A fast heating takes place as response to the first pulse, followed by cooling before the next pulse hits the sample volume. Over the pulse train a successive heating can be observed for certain dose-fluence regimes (25, 26, 29). Thus, the PNIPAm shell’s collapse is expected to be triggered by this heating, as schematically represented in Fig.
85 1. The systems studied here are composed of silica-core – PNIPAm-shell nanoparticles synthesized with two different cross-linker concentrations, 4 and 8 weight percent of methylenbisacrylamide (BIS) and two different shell thicknesses (~ 125 nm for the thinner and ~ 160 nm for the thicker shell), see materials and methods and Supplementary Materials for more details. The systems have been characterized by Dynamic Light Scattering (DLS) to track the variation of
90 the particles’ radii with temperature, see the inset in Fig. 1. These DLS measurements showed a Lower Critical Solution Temperature (T_{lcs}) of ~ 312 K for all samples. Since the difference in electron density between the polymer and water is negligible compared to the one between




Figure 1: **Conceptual scheme of the experiment.** Central panel: the train of X-ray pulses reaches the sample and heats it up in a controlled manner (red line in the right plot). If the silica nanoparticles are covered by PNIPAm, then the series of pulses will trigger the transition from the swollen hydrophilic to the collapsed hydrophobic state. In the top-left plot a typical DLS characterization of one of our core-shell system is displayed, specifically a sample at high cross-linker concentration and thin shell thickness of 34 nm in the collapsed state.

water and silica, the information of the scattered intensity $I(q)$, where q is the exchanged wave vector, is dominated by the silica core in the accessible q -range (see SM). Even after the complete collapse of the PNIPAm shell shows only small changes in a region with very low count rates and consequently are affected by substantial systematic errors. Therefore, all the information on the kinetics of the microgel collapse is encoded in the changes in the dynamics of the particles.

2.1 Effects of fluence and controlled heating

The response of the nanoparticles is critically dependent on the X-ray intensity per pulse. Changes can be easily observed from the Two-Times Correlation Matrices (TTCM) obtained by XPCS which are a powerful tool to measure the non-equilibrium dynamics (30). Details of the XPCS approach used here are given in the methods section. A broadening of the diagonal implies a slowing down of the dynamics in the scattering volume, as found e.g. in aging glasses (31–33). Similarly, a narrowing implies a speeding up of the dynamical processes, as can be seen from Fig. 2(c). Selecting sections of the TTCM it is then possible to obtain a quantitative description of the non-equilibrium dynamics accessing information dependent on the time elapsed since the beginning of the measurement t_w , which in this context means the time interval between the observed dynamical quantity and the first pulse that reached the sample. The most common way to characterize this time-dependent dynamics is to fit a Kohlrausch–Williams–Watts (KWW) function $g_2(t) - 1 = \beta_q \cdot \exp(-(t/\tau)^\gamma)$ to the data, where τ is usually a function of q and eventually of t_w . For diffusive systems $\gamma \approx 1$ and $\tau(q) \propto q^{-2}$. In systems such as the ones investigated here β_q is a quantity that depends on the instrument parameters (34) that have been characterized elsewhere (35). In Fig. 2 (a) we report the two-times correlation matrix for a sample with 8 wt% and thick shell taken at $q = 0.087 \text{ nm}^{-1}$ and fluence of $F = 1.85 \text{ mJ/mm}^2$ per pulse (in the manuscript all fluence values are reported per pulse). As the width of the diagonal is constant at this fluence regime the dynamics of the particles remains stationary within a train. This is confirmed by the time-resolved intensity-intensity correlation functions $g_2(t_w, t)$ starting at different time points t_w within the pulse train, see Fig. 2(b). The data shown here was obtained by averaging the first and last $30 \mu\text{s}$ of the TTCM. Despite the noisiness of the data points, a consequence of the low pulse intensity, it is possible to see how the sample relaxes following the same single exponential behaviour at the beginning and at the end of the train. We conclude that at least up to a certain fluence of about 2 mJ/mm^2 the system remains at equilibrium and the change in temperature is too weak to be detected by the change in the dynamics at the probed length-scales. Therefore, for measurements in this fluence regime the relaxation time only depends on q .

Increasing the fluence to 19.1 mJ/mm^2 , the TTCM shows a completely different behavior as shown in Fig. 2(c). The dynamics sharply speeds up in less than $100 \mu\text{s}$ in a non-linear fashion. In Fig. 2(d) the corresponding $g_2(t_w, t)$ functions obtained from slices averaged over 10 pulses ($2.6 \mu\text{s}$) at $t_w = 4 \mu\text{s}$ and $t_w = 80 \mu\text{s}$ are displayed. The relaxation in the first part of the train is described by a KWW function with a compressed exponential with value of

$\gamma = 1.65$, indicating that the dynamics is better described by a ballistic motion than diffusion. Towards the end of the train, the apparent drop in contrast is due to a faster relaxation combined with a stretched KWW exponent ($\gamma \approx 0.5$) indicating a wide distribution of relaxation times in the same scattering volume. Qualitatively, this situation is similar to what has been observed already in suspensions of pure silica nanoparticles and could be connected to heating of the particles and the surrounding water (25), where for more intense fluences the dynamics was markedly faster already after few pulses.

To extract more detailed information from the correlation functions, we analyzed the KWW shape parameter γ as a function of q and t_w for different fluences. In Fig. 3(a) the average relaxation time $\langle \tau(q) \rangle = \Gamma_0(1/\gamma)\tau(q)/\gamma$, where Γ_0 is the gamma function, is reported for two runs at two representative fluences. The low fluence does not produce strong temperature changes within a train and consequently the relaxation times follow the Stokes-Einstein relation with a diffusion constant of $1.9 \pm 0.1 \text{ nm}^2/\mu\text{s}$, compatible with a swollen particle at 303 K. Conversely, the high fluence data show a decrease of the relaxation times for increasing t_w (or number of pulses n_p). In Fig. 3(b) the shape parameters of the relaxation functions at different t_w are reported for both fluences. While the data at lower fluences do not deviate from the exponential shape (i.e. $\gamma = 1$ expected for freely diffusing particles), we observe for larger fluences a $\gamma > 1$ for the initial pulses and a normal diffusive regime after few pulses indicating a change of the relaxation from compressed to simple exponential and eventually to stretched, as discussed above. This suggests that the initial pulses induce a ballistic-like motion of the nanoparticles that quickly subsides in a diffusive behaviour at later stages. The transition to a stretched exponent indicates the presence of a large distribution of relaxation times within the scattering volume. In a dilute system, as the one probed here, this means that each particle diffuses with a different diffusion constant. A similar behaviour was observed for pure silica particles (25) and was attributed to the profile of the incident radiation and thus a heterogeneous temperature in the probed volume. However, in the present system stretched relaxation may also indicate sample damage and deviations from the Stokes-Einstein relation, e.g. as a consequence of aggregation. To shed more light on these effects we take analyze the changes in diffusivity as a function of t_w , see methods for further details.

2.2 Diffusion constant and effective temperature

The change of relaxation time is the combined effect of both the rising local temperature and the collapse of the PNIPAm shell. From the measurements of the relaxation time at different fluences we can obtain the change of the diffusion constant D for different t_w (or n_p). As D is a function of temperature, both fluence and repetition rates contribute to the local "effective temperature" T_{eff} experienced by the particle (25, 26). The key concepts at the basis of the "time-resolved" model are that the observed diffusion is affected by the changes in temperature, and consequently viscosity, in the first few nanometers of water surrounding the particles produced by the heating of the particles themselves. The model, developed for aqueous dispersions of silica nanoparticles, can be employed also in this situation under the assumption that




Figure 2: **Examples of the observed dynamics at $q=0.087 \text{ nm}^{-1}$ in two fluence regimes.** (a) and (c) show the TTCM for a low fluence (1.84 mJ/mm^2) and a high fluence (19.12 mJ/mm^2) measurement. (b) and (d) show the corresponding time-resolved correlation functions $g_2(t_w, t)$ at two t_w : orange circles shows a t_w at the beginning of the train, blue diamonds a t_w at the end of the train. To fit the blue points in (d) both baseline and contrast were kept fixed at the values obtained from the fit at the beginning of the train.




Figure 3: **Relaxation times and KWW exponents for samples with thin shell and BIS 8 wt%.** (a) Relaxation times as a function of q for two fluences. For $F = 1.85 \text{ mJ/mm}^2$ the average over the whole TTCM is displayed. The black line is the fit of the Stokes-Einstein relation and returns a diffusion constant of $1.9 \pm 0.1 \text{ nm}^2/\mu\text{s}$. The colored data are the pulse-resolved average relaxation times for $F = 12.2 \text{ mJ/mm}^2$. (b) KWW exponent at different t_w for two fluences of $F = 12.2 \text{ mJ/mm}^2$ and $F = 3.51 \text{ mJ/mm}^2$.

the difference between the X-ray absorption coefficient of the hydrated PNIPAm shell and water is small and therefore negligible. Using a known set of pure silica nanoparticles as a calibrant (see S.M. and refs. (26, 36)) we evaluate the actual X-ray fluence delivered to the sample and thus the effective temperature. In the following, we distinguish four fluence regimes: regime F1 with $F < 2 \text{ mJ/mm}^2$, regime F2 with $2 \text{ mJ/mm}^2 \leq F < 5 \text{ mJ/mm}^2$, regime F3 with $5 \text{ mJ/mm}^2 \leq F < 13 \text{ mJ/mm}^2$ and regime F4 with $F \geq 13 \text{ mJ/mm}^2$. As shown in Fig. 2, for F1 the diffusive dynamics do not vary over the pulse trains, suggesting no impact of beam-induced heating. Fig. 4 shows D as a function of T_{eff} for one sample studied at three repetition rates and different fluences (regimes F2, F3, F4). The experimental data are compared to the limit values, represented as lines in Fig. 4, that correspond to the diffusivity of completely swollen (blue solid line), fully collapsed (red dot-dashed line) and pure silica core (black dashed line) particles.

For F1 the average dynamics is stationary with only an increase of few degrees above room temperature and still below the T_{lcst} . At moderate fluences (regime F2), reported in Fig. 4(a), the diffusion constant deviates from the behaviour of swollen particles. At 1.125 MHz repetition rate, a transition from swollen to collapsed particles can be observed over the pulse train. In contrast, the diffusivities at 2.24 MHz are already close to the collapsed line at small T_{eff} . This indicates that the particles have a smaller hydrodynamic radius, e.g. they have lost part of the PNIPAm shell. For regime F3, see Fig. 4(b), again the diffusivities at 2.24 MHz are close to,

or above, the line of fully collapsed particles while the 1.125 MHz data change from swollen to collapsed. Interestingly, the diffusivities measured at 0.55 MHz reach the line of collapsed particles at lower T_{eff} than the 1.125 MHz. Fig. 4(c) shows data for fluence regime F4. Here, data taken at both 1.125 MHz and 0.55 MHz display only the collapsed behaviour while the diffusion of the 2.24 MHz is compatible with particles whose size corresponds to the pure silica core. At later times (i.e. higher T_{eff}) all of the datasets deviate from these regimes, suggesting the accumulation of sample damage within a train.

The data shows that the combination of high repetition rate and high fluence (F4) completely destroys the shell, while samples probed at lower repetition rates survive these higher dose rates. This effect can be qualitatively understood remembering the fact that the collapse of the shell is a phase transition from a hydrophilic state to a hydrophobic one and that the collapse in itself requires a finite time to happen. At those fluences each XFEL pulse carries enough energy to heat up the core silica particle and the surrounding volume well above $T_{\text{lcst}} = 312$ K. At the same time it will produce a certain amount of damage, poking holes in the polymer network. If the PNIPAm is still fully hydrated, the self-diffusivity is high, and it will be easier for damaged sections of the shell to escape and diffuse into the solvent and eventually forming smaller nanogels. Conversely, if the PNIPAm is already in a collapsed state, it will be more difficult for the damaged parts to escape because of reduced diffusivity within the network and the hydrophobicity. Therefore, looking at the diffusivity of the particles, and thus their hydrodynamic radius, it would appear that the collapsed particles maintain a substantially higher damage threshold. When the second pulse reaches a system of already collapsed particles it will basically heat up the surrounding water similarly to Refs. (25, 26). In contrast, if the shells of the particles are not yet collapsed it will aggravate the damage and after the initial ballistic phase the majority of the particles will have their shells completely removed. This suggests that the time required for a shell to collapse must be smaller than $0.88 \mu\text{s}$ (1.125 MHz) but not too different from $0.44 \mu\text{s}$ (2.24 MHz). Therefore, the diffusion constant is a quantity that depends not only on T_{eff} but also on the timescale. A direct consequence of this time-dependency is visible in Fig. 4(b), where the 0.55 MHz data reach the "collapsed line" at lower T_{eff} than the data taken at 1.125 MHz. In fact, for 0.55 MHz each T_{eff} is separated by a larger time interval allowing a more complete collapse between the pulses. This is in accordance with observations that both the collapsing and swelling times are connected with the diffusion of water in a complex environment such as the polymer network of the PNIPAm shell (10, 13). It is interesting how this damage threshold is associated with a dose-rate rather than a total dose. Previous studies performed at SACLA on similar systems of silica core-PNIPAm shell identified a damage threshold at $4 \cdot 10^2$ kGy (37). The damage was observed in changes of the $I(q)$ showing signs of agglomeration. In the F4 regime the dose delivered by a single pulse was about 8.8 kGy and the threshold of Ref. (37) is reached after 46 pulses. The existence of a total dose threshold is visible also in our dynamical data and can be identified with the violation of the Stokes-Einstein relation in the $D(T_{\text{eff}})$ plots of Fig. 4. In the specific case of 1.125 MHz data, this violation appears at ~ 57 pulses, thus $\sim 5 \cdot 10^2$ kGy, reported in Figure S4 of the SM. The violation of the Stokes-Einstein relation in this case is likely due to substantial

changes within the scattering volume, e.g. changes in viscosity as a consequence of fragments produced by the damaged PNIPAm or the initial steps of the formation of large aggregates. The mismatch between our threshold and the one reported in (37) is due to the fact that the latter experiment was performed at 10 Hz, thus observing timescales much longer than what can be
 235 accessed here (few hundreds of microseconds).

Next, we take a closer look on the measured $D(T_{\text{eff}})$ for a collapsing PNIPAm shell. Following the reasoning reported in (12) we can extend the "time-resolved" model illustrated in (25) by adding a temperature- and time- dependent radius. The temperature dependence is obtained by a parametrization of the equilibrium response measured at macroscopic length-scales by
 240 DLS while a time dependence is introduced with two exponential relaxations that delays all changes of the PNIPAm length. In Fig. 5(a) the calculated local temperature experienced by a nanoparticle is reported. Further details of the temperature model can be found in the SM. In short, assuming a spherical particle, it is possible to analytically describe the temperature as a function of both time and distance from the center of the particle with:

$$T(t, r) = \frac{\Delta T}{r/R_0} e^{-\Gamma_c t} + T_0, \quad (2)$$

where R_0 is the particle's radius, ΔT is the temperature jump produced by the absorption of the X-rays, T_0 is the temperature before the pulse and Γ_c is the thermal relaxation rate. In Fig. 5 we use $\Gamma_c = 4.6$ MHz and $\Delta T = 14$ K, which are typical values for $F \approx 13$ mJ/mm². The temperature changes as a function of distance from the particle's surface and eventually it crosses T_{lcst} within the length of the PNIPAm polymer. To account for this situation the
 250 thickness of the PNIPAm polymer ($L_P(t)$) is divided into N segments calculated as follows:

$$L_P(t) = \sum_{i=1}^N l_i(T(t, r_i)) \quad (3)$$

where $r_i = \sum_{j=0}^i l_j$ is the sum of all the previous segments starting from the particle's surface.

In the inset of Fig. 5(a) we report the PNIPAm elongation as a function of time. The blue line is the result for a polymer that can follow instantaneously all temperature changes, while the red line is the elongation of a polymer that can collapse and swell exponentially
 255 with finite characteristic times τ_{collapse} and τ_{swell} . In this example we set $\tau_{\text{collapse}} = 10$ ns and $\tau_{\text{swell}} = 800$ ns. The calculated radius is used to compute an instantaneous diffusion constant which is averaged over the time interval between two pulses. In Fig. 5(b) the experimental data points for the thick shell 8% BIS sample at 1.1 MHz are reported together with the output of the model (dot dashed lines). For the lower fluences of regime F2, the model predicts a
 260 behaviour similar to the one expected from an instantaneous response of the PNIPAm shell (black continuous line), while the data points show already a partial collapse. At such fluences, the pulses are not strong enough to rise the local temperature above T_{lcst} and the particles are affected mostly by the temperature of the surrounding water. Upon increasing the fluence the




Figure 4: **Diffusion constant for samples with thick shell and BIS 8 wt% as a function of T_{eff} for different repetition rates and different fluences.** (a) Low fluence limit of regime F2, for comparison the measured diffusion constant obtained from an F1 run is also reported (black star). Due to the limited signal to noise ratio only data for 1.1 MHz and 2.2 MHz are reported. (b) Intermediate fluences (regime F3). (c) High fluences (regime F4). The lines represent the limit values for the completely swollen (solid blue), fully collapsed (dash-dotted red) and pure silica core (dashed black) state.




Figure 5: **Results from time-resolved model.** (a): Calculated temperature as a function of r/R_0 and t after a temperature jump of 14 K. In the inset the calculated elongations of the PNIPAm chains are reported for a situation in which there is no delay in the response (blue) and a delay of 10 ns and 800 ns in the collapse and reswelling, respectively. (b): Model results for 1.1 MHz data and thick shell 8 wt% BIS compared with the experimental data (model:dot-dashed lines; data: circles). The dashed lines are limit values that mark the diffusion of swollen (blue) and collapsed (red) particles. The black line represents the instantaneous response limit.

$R(T = 296K)$	$R(T = 315K)$	BIS %	τ_{collapse}	τ_{swell}
$156 \pm 3 \text{ nm}$	$83 \pm 5 \text{ nm}$	8 wt%	$595 \pm 50 \text{ ns}$	$\geq 80 \mu\text{s}$
$157 \pm 4 \text{ nm}$	$81 \pm 8 \text{ nm}$	4 wt%	$198 \pm 20 \text{ ns}$	$\geq 100 \mu\text{s}$
$129 \pm 3 \text{ nm}$	$79 \pm 7 \text{ nm}$	8 wt%	$496 \pm 34 \text{ ns}$	$\geq 60 \mu\text{s}$
$122 \pm 4 \text{ nm}$	$86 \pm 8 \text{ nm}$	4 wt%	$495 \pm 22 \text{ ns}$	$\geq 60 \mu\text{s}$

Table 1: Summary of the parameters of the investigated samples and results from the fitting procedure. The radii are obtained from the DLS characterizations reported in the SM. The values of τ_{swell} are the lower limits for the swelling times.

predicted diffusivity departs from the "instantaneous response" until it reaches a behaviour in which the transient temperature gradient surrounding the particles and the internal characteristic times of the polymer shell play a major role, describing a behaviour more in agreement to the data. The fact that the data points seems to follow the same master curve, suggests that even weak pulses are able to trigger a collapse of the shell.

The model does not provide predictions outside of the time-resolved evolution of the temperature surrounding the particles, and more complete theoretical descriptions are beyond the aim of this work. However, despite its simplicity it is possible fit it to the experimental data at F3 fluence regime to estimate the characteristic times τ_{collapse} and τ_{swell} of the polymeric shell. In Fig. 6(a) and (b) the data at fluences in the F3 regime are reported together with the corresponding fits of the models for the set of samples. In Fig. 6(a) the data for the thinner shell are reported, while Fig. 6(b) shows the data for the thicker shell. It is possible to track how the collapse is triggered at low T_{eff} values in all cases. In those fits the only free parameters were τ_{collapse} and τ_{swell} , while $R(T_{\text{eff}})$ was determined by previous DLS characterization, see table 1 where the particles' radii and the results from the fit of τ_{collapse} are reported. It is important to notice that in the data the parameters τ_{collapse} and τ_{swell} are correlated. In fact, since the diffusion constant is sampled at a given rate, i.e. the diffusion is only probed at time intervals defined by the EuXFEL repetition rate, every combination of τ_{collapse} and τ_{swell} that gives the same PNIPAm length in the time interval between two pulses will produce the same result. There are however two limits of the set of possible solutions for which these two parameters become independent: one for a fast τ_{collapse} (below $\sim 10 \text{ ns}$) and one for a slow τ_{swell} , above $\sim 80 \mu\text{s}$. The former limit corresponds to an almost instantaneous collapse process, while the latter represent a condition in which the system is not able to recover within the time interval between two pulses. Considering that in the previous section we concluded that the time required for the shell collapse must be close to 440 ns (2.24 MHz repetition rate), the more likely scenario is the one for slow τ_{swell} . Under this assumption the resulting τ_{collapse} are reported in Fig. 6(c). A high concentration of cross-linkers slows down the collapse process, suggesting that a stiffer shell requires more time to reach a collapsed configuration.

According to Tanaka's model both τ_{collapse} and τ_{swell} should scale with the square of the swollen PNIPAm radius even for core-shell nanoparticles (11). In Fig. 6 (c) we report our results together with the literature values from (7) and references therein as well as Tanaka's




Figure 6: **Fitted models and results compared with literature.** (a): data for thinner shell and different BIS concentrations, data at 8 wt% BIS (blue squares) are obtained from 1.125 MHz runs while 4 wt% BIS (orange hexagons) were obtained from 0.55 MHz runs because for technical reasons it was not possible to measure F3 data for the latter sample. (b): data for 1.125 MHz runs for thicker shell at different BIS concentrations of 4 wt% (red circles) and 8 wt% (green diamonds). The fits shown here used a fixed $\tau_{swell} = 80 \mu s$ (dashed lines of respective colours). (c): Results of the present work, diamonds and triangles, reported together with literature values from (7) (stars) and references therein (circles). The line is a linear fit to the literature data and the shaded area is the confidence band.

model. Roughly speaking, it is possible to group the measurements of the PNIPAm kinetics into two main categories, global heating, where the temperature jump is applied to the water and local heating, where the temperature jump is applied directly to the particles. It is clear to see that $\tau_{collapse}$ deviates from the general trend observed for the global heating experiments (blue circles) and is instead closer to the local heating obtained with ns laser pulses tuned at the plasmon resonance of the core particles. This can be expected since both experiments exploit the local heating of the cores to trigger the phase transition. In contrast to the other studies, we observed a strong difference between swelling and deswelling timescales. The lower limits for the swelling times fall close to the points observed for global heating experiments. The X-rays slightly heat up also the water in the scattering volume. Considering that the timescales necessary to dissipate the heat is on the order of hundreds of microseconds (see supporting information of (26)), the situation is more similar to the one of global heating experiments. It is worth noticing that even in the opposite limit of the possible solutions for our fit ($\tau_{collapse} \sim 10$ ns and $\tau_{swell} \sim 1 \mu s$) the results would remain qualitatively the same, with a collapse time close to the local heating experiments and a swelling time close to the global heating ones.

3 Discussion

Thanks to the short wavelengths and the MHz repetition rates of the European XFEL, we could access the time and temperature evolution of the diffusion coefficient of silica/core-PNIPAm/shell nanoparticles when the PNIPAm undergoes a solubility phase transition induced by a change in (local) temperature above T_{lcst} . We observed the presence of two damage thresholds, one related to the accumulated dose which is compatible with the values observed in previous experiments (37) and one which depends both on the dose rate and on the repetition rate, from which we can infer an upper limit on the characteristic collapsing time. It is interesting to point out how the latter damage threshold is observed at much lower total doses. For the sake of discussion it is interesting to consider also another interpretation of the 2.2 MHz data in fluence regimes F2 and F3. In this interpretation the particles would not be damaged but in an “over-collapsed” state. In fact in equilibrium conditions, PNIPAm retains a certain amount of water in its volume even above the T_{lcst} (38). Within this alternative interpretation, the high repetition rates would induce a squeeze out of this remaining water content resulting in particles with an effectively smaller hydrodynamic radius. Consequently, the collapsing time of the PNIPAm shell should be on the order of ~ 10 ns, which is still consistent with our model. This “over-collapse” interpretation is however highly speculative, and would lead to the counter-intuitive result that higher dose-rates are in practice less harmful to the sample. For this reason we consider it unlikely but nevertheless we believe it might be a target of investigation for other experiments.

Adapting a phenomenological model previously developed to this system we were able to observe that the phase transition happens even at relatively low local temperatures, suggesting an effective lowering of T_{lcst} , whose origin is still unclear. Given the characteristics of the system, the creation of free charges after the absorption of the X-rays should play a role, while charges in solution lower the T_{lcst} (39, 40), charges embedded in the polymer network lead to the opposite effect (41, 42) and the two effects influence each other (43). With our model we were able to fit the data and extract $\tau_{collapse}$ and τ_{swell} . While $\tau_{collapse}$ is consistent with results from laser heating of gold cores of gold-PNIPAm nanoparticles, the swelling times τ_{swell} resemble the ones of global heating experiments. This indicates that the X-ray induced heating process with successive cooling differs from local and global heating processes studied so far. Moreover, we were able to observe an effect of the concentration of cross-linkers on the kinetic response of the polymer, effectively slowing down the collapse for larger concentrations. It is worth noticing that this kind of information has been obtained from diffusion experiments coupling the possibility to probe non-equilibrium systems with XPCS with the MHz and nm time- and length-scale reachable at European XFEL. These findings are important not only for the investigation of the kinetics of the PNIPAm collapse, but also for future studies where the collapse and swelling are triggered in more complex environments. More in general, the advancement of these techniques and their successful application to more and more radiation sensitive systems is a great asset for investigations tackling biologically relevant phenomena such as protein folding kinetics.

4 Materials and Methods

4.1 XPCS technique

Coherent and partially-coherent electromagnetic radiation, once diffused by a random media, produces an interference phenomenon also known as speckle-pattern. The speckle pattern encodes the density fluctuations of the material that generated it and can be used to access the intermediate scattering function (44). More in detail, in a generic XPCS measurement one collects the scattered intensity within a given time interval (here determined by the XFEL pulse duration, thus ≈ 50 fs) at a certain q , thus selecting an appropriate region of interest (ROI). One can compute the two-time correlation matrix ($C_q(n_1, n_2)$) as follows:

$$C_q(n_1, n_2) = \frac{\langle I_{pix}(n_1) I_{pix}(n_2) \rangle_{pix}}{\langle I_{pix}(n_1) \rangle_{pix} \langle I_{pix}(n_2) \rangle_{pix}} - 1, \quad (4)$$

where $\langle \dots \rangle_{pix}$ denotes the average over the pixels within the same q -ROI, $n_{1,2}$ indicates the number of frames collected since the beginning of the measurement and $I_{pix}(n)$ is the intensity recorded at pixel pix at frame number n . Typically, one finds the two-time correlation matrix expressed as a function of time that is obtained straightforwardly via $t_{1,2} = \delta t n_{1,2}$, where δt is the time interval between two frames. For stationary systems the dynamics depends only on lag time $t = |t_2 - t_1|$ and it is possible to average $C_q(t_1, t_2)$ along its diagonals in order to obtain the more common autocorrelation function $g_2(t) - 1$. It can be demonstrated that $g_2(t) - 1$ is proportional to the square modulus of the intermediate scattering function, with a proportionality constant given solely by experimental parameters (34). In general one can describe $g_2(t) - 1$ with a Kohlrausch–Williams–Watts (KWW) function (or stretched exponential) $g_2(t) - 1 = \beta_q \cdot \exp(-(t/\tau)^\gamma)$. The simple diffusion is a particular case of this KWW where $\gamma = 1$ and $1/\tau = q^2 D$. For non-stationary dynamics the two-time correlation matrix ceases to depend solely on t and will become a function of another time, often indicated as the "age" t_w . There are several ways to map the $C_q(t_1, t_2)$ into the $C_q(t_w, t)$, see for example (30), here the convention $t_w = t_1$ and $t = t_2 - t_1$ is followed. For non stationary dynamics with age-dependent parameters we can then write (45, 46):

$$C_q(t_w, t) = \beta_q \exp(-(t/\tau(q, t_w))^\gamma). \quad (5)$$

To take in account the change in shape of the relaxations, the average relaxation time is considered, obtaining a set of $\langle \tau \rangle$ for each t_w and q . Then, each set of $\langle \tau \rangle$ is fitted by $1/(D(t_w)q^2)$ and to discriminate between the ballistic-like and diffusive dynamics, the fits with an R -squared lower than 0.85 were rejected. Then, the diffusion constant is calculated again for each accepted $\langle \tau(q, t_w) \rangle$ and the standard deviation is used to estimate the uncertainty over $D(t_w)$.

4.2 Synthesis details

Synthesis of silica nanoparticles: 352 ml of ethanol + 3.4 ml of ammonium hydroxide (28-30%) + 54 ml ultra-pure water were vigorously stirred in a 1L Erlenmeyer flask. Afterwards,

29.0018 g of tetraethyl orthosilicate (TEOS) + 60 ml of ethanol were added quickly and the
385 reaction was let to proceed for approx. 24 h. In the next step, coating with 3-trimethoxysilyl
propyl methacrylate was undertaken. For that 8 ml of 3-trimethoxysilyl propyl methacrylate
were dissolved in 10 ml of ethanol and added dropwise to the reaction flask. Reaction was
let to proceed for another 24 h. After that the suspension was concentrated using a rotational
evaporator and then dialized against ethanol for 1 week. The whole procedure was carried
390 out at room temperature. A portion of these silica nanoparticles in ethanol was measured in a
separate SAXS experiment performed at a synchrotron beamline (P10 at PETRA III). From that
characterization it was possible to determine that the core particles are spheres with average
radius $R_0 = 43.3 \pm 0.1$ nm and size distribution $\Delta R/R_0 = 0.10 \pm 0.01$.

For the shell synthesis: 500 ml of water was heated up to 60 °C in an oil bath. Then, under
395 nitrogen flow, a mixture of 0.126g of sodium dodecyl sulfate and 0.139 g sodium sulfite together
with 15 ml of the silica nanoparticles dispersed in ethanol was injected. Everything was stirred
at 60 °C under nitrogen for 1 h. After that, 0.135g of potassium peroxodisulfate and 4 mg of
ammonium iron(II) sulfate hexahydrate dissolved in 3-5 ml of water were added. Immediately
afterwards, 1 g (1.5 g) of N-isopropylamide, for the thin and thick shells respectively, and the
400 corresponding quantities of N,N'-methylenbisacrylamide to reach the BIS concentrations of 4
wt% and 8 wt% were dissolved in 20 ml of EtOH and added dropwise, the overall time for the
addition was approximately 10 minutes. The reaction was left to proceed for 24 h, and after that
the suspension was concentrated and dialyzed against water for 1 week. The dispersions used
for the results reported here, had mass concentrations between 3 wt% (thin shell BIS 4 wt%)
405 and 4 wt% (thick shell BIS 8 wt%). The corresponding volume fractions in the swollen state
were $\sim 12\%$ and $\sim 25\%$ for the thin and thick shell respectively, while in the collapsed state
the volume fractions were $\sim 2.8\%$ and $\sim 3.5\%$. In all cases the concentration was low enough
to have freely diffusing particles with no short-range order, i.e. $S(Q) \approx 1$, as can be inferred
from (24).

410 Lastly, the colloidal dispersions were filled into thin-walled quartz capillaries with an outer
diameter of 1.5 mm that were sealed and placed in a specifically designed sample-holder. The
experiment was performed in air at the MID instrument. A detailed description of the instrument
can be found in (47).

4.3 Set-up

415 The experiment has been carried out in two rounds, in both rounds the photon energy was set
to 9 keV. The intensity of the X-ray pulses was measured with a gas monitor placed upstream
the sample position. The beam-size at the sample position was about 8 μm and 10 μm in di-
ameter in the first and second round respectively, obtained by focusing the beam by compound
refractive lenses (CRL). The X-ray fluence was controlled with stacks of chemically vapour de-
420 posited (CVD) diamond plates that could be inserted to absorb the beam. For the data reported
here the total thicknesses ranged from 2.5 mm to 7.05 mm. Taking the beamline and air trans-
mission into account, the intensities on sample were reduced by a factor ranging from 1.2×10^{-4}

to 1.5×10^{-3} with respect to the one measured with the gas monitor. The scattered intensity was recorded with an Adaptive Gain Integrating Pixel Detector (AGIPD) mounted downstream the sample. Distance and relative positions of the four detector quadrants were determined with the aid of a known reference sample measurement measured also at a well-characterized synchrotron beamline (36). A sample-detector distance of 7.381 m was determined this way. The samples were placed in sealed quartz capillaries and measured in air at room temperature.

References and Notes

1. M. Karg, A. Pich, T. Hellweg, T. Hoare, L. A. Lyon, J. J. Crassous, D. Suzuki, R. A. Gumerov, S. Schneider, I. I. Potemkin, W. Richtering, Nanogels and microgels: From model colloids to applications, recent developments, and future trends, *Langmuir* **35**, 6231-6255 (2019). PMID: 30998365.
2. M. C. Koetting, J. T. Peters, S. D. Steichen, N. A. Peppas, Stimulus-responsive hydrogels: Theory, modern advances, and applications, *Mat. Sci. Eng. R* **93**, 1-49 (2015).
3. M. A. C. Stuart, W. T. S. Huck, J. Genzer, M. Müller, C. Ober, M. Stamm, G. B. Sukhorukov, I. Szleifer, V. V. Tsukruk, M. Urban, F. Winnik, S. Zauscher, I. Luzinov, S. Minko, Emerging applications of stimuli-responsive polymer materials, *Nat. Mater.* **9**, 101-113 (2010).
4. P. J. Yunker, K. Chen, M. D. Gratale, M. A. Lohr, T. Still, A. G. Yodh, Physics in ordered and disordered colloidal matter composed of poly(n-isopropylacrylamide) microgel particles, *Rep. Prog. Phys.* **77**, 056601 (2014).
5. J. Brijitta, P. Schurtenberger, Responsive hydrogel colloids: Structure, interactions, phase behavior, and equilibrium and nonequilibrium transitions of microgel dispersions, *Curr. Opin. Colloid In.* **40**, 87–103 (2019).
6. F. Scheffold, Pathways and challenges towards a complete characterization of microgels, *Nat. Commun.* **11** (2020).
7. J. Zhao, H. Su, G. E. Vansuch, Z. Liu, K. Salaita, R. B. Dyer, Localized nanoscale heating leads to ultrafast hydrogel volume-phase transition, *ACS Nano* **13**, 515-525 (2019).
8. K. Nothdurft, D. H. Müller, S. D. Mürztz, A. A. Meyer, L. P. B. Guerzoni, A. Jans, A. J. C. Kühne, L. De Laporte, T. Brands, A. Bardow, W. Richtering, Is the microgel collapse a two-step process? exploiting cononsolvency to probe the collapse dynamics of poly-n-isopropylacrylamide (pnipam), *J. Phys. Chem. B* **125**, 1503-1512 (2021). PMID: 33503378.
9. M. Annaka, C. Yahiro, K. Nagase, A. Kikuchi, T. Okano, Real-time observation of coil-to-globule transition in thermosensitive poly(n-isopropylacrylamide) brushes by quartz crystal microbalance, *Polymer* **48**, 5713-5720 (2007).

10. J. Wang, D. Gan, L. A. Lyon, M. A. El-Sayed, Temperature-jump investigations of the kinetics of hydrogel nanoparticle volume phase transitions, *J. Am. Chem. Soc.* **123**, 11284-11289 (2001). PMID: 11697971.
- 460 11. J. Wahrmund, J.-W. Kim, L.-Y. Chu, C. Wang, Y. Li, A. Fernandez-Nieves, D. A. Weitz, A. Krokhin, Z. Hu, Swelling kinetics of a microgel shell, *Macromolecules* **42**, 9357-9365 (2009).
12. S. Murphy, S. Jaber, C. Ritchie, M. Karg, P. Mulvaney, Laser flash photolysis of au-pnipam core-shell nanoparticles: Dynamics of the shell response, *Langmuir* **32**, 12497-12503
465 (2016). PMID: 27778508.
13. B. Tadgell, E. Ponomareva, M. Karg, P. Mulvaney, Temperature-jump spectroscopy of gold-poly(n-isopropylacrylamide) core-shell microgels, *J. Phys. Chem. C* **126**, 4118-4131 (2022).
14. R. Keidel, A. Ghavami, D. M. Lugo, G. Lotze, O. Virtanen, P. Beumers, J. S. Pedersen,
470 A. Bardow, R. G. Winkler, W. Richtering, Time-resolved structural evolution during the collapse of responsive hydrogels: The microgel-to-particle transition, *Sci. Adv.* **4**, eaao7086 (2018).
15. K. Otake, R. Karaki, T. Ebina, C. Yokoyama, S. Takahashi, Pressure effects on the aggregation of poly(n-isopropylacrylamide) and poly(n-isopropylacrylamide-co-acrylic acid) in aqueous solutions, *Macromolecules* **26**, 2194-2197 (1993).
475
16. N. Osaka, M. Shibayama, T. Kikuchi, O. Yamamuro, Quasi-elastic neutron scattering study on water and polymer dynamics in thermo/pressure sensitive polymer solutions, *J. Phys. Chem. B* **113**, 12870-12876 (2009).
17. M. Shibayama, K. Isono, S. Okabe, T. Karino, M. Nagao, SANS study on pressure-induced phase separation of poly(n-isopropylacrylamide) aqueous solutions and gels,
480 *Macromolecules* **37**, 2909-2918 (2004).
18. L. Tavagnacco, E. Chiessi, E. Zaccarelli, Molecular insights on poly(n-isopropylacrylamide) coil-to-globule transition induced by pressure, *Phys. Chem. Chem. Phys.* **23**, 5984-5991 (2021).
- 485 19. T. Tanaka, D. J. Fillmore, Kinetics of swelling of gels, *J. Chem. Phys.* **70**, 1214-1218 (1979).
20. E. Sato Matsuo, T. Tanaka, Kinetics of discontinuous volume-phase transition of gels, *J. Chem. Phys.* **89**, 1695-1703 (1988).
21. F. Lehmkuhler, W. Roseker, G. Grübel, From femtoseconds to hours—measuring dynamics
490 over 18 orders of magnitude with coherent x-rays, *Appl. Sci.* **11**, 6179 (2021).

22. V. Nigro, B. Ruzicka, B. Ruta, F. Zontone, M. Bertoldo, E. Buratti, R. Angelini, Relaxation dynamics, softness, and fragility of microgels with interpenetrated polymer networks, *Macromolecules* **53**, 1596–1603 (2020).
- 495 23. L. Frenzel, F. Lehmkuhler, M. Koof, I. Lokteva, G. Grübel, The phase diagram of colloidal silica–PNIPAm core–shell nanogels, *Soft Matter* **16**, 466–475 (2020).
24. L. Frenzel, M. Dartsch, G. M. Balaguer, F. Westermeier, G. Grübel, F. Lehmkuhler, Glass-liquid and glass-gel transitions of soft-shell particles, *Phys. Rev. E* **104**, 1012602 (2021).
- 500 25. F. Lehmkuhler, F. Dallari, A. Jain, M. Sikorski, J. Möller, L. Frenzel, I. Lokteva, G. Mills, M. Walther, H. Sinn, F. Schulz, M. Dartsch, V. Markmann, R. Bean, Y. Kim, P. Vagovic, A. Madsen, A. P. Mancuso, G. Grübel, Emergence of anomalous dynamics in soft matter probed at the european XFEL, *Proc. Natl. Acad. Sci.* **117**, 24110–24116 (2020).
- 505 26. F. Dallari, A. Jain, M. Sikorski, J. Möller, R. Bean, U. Boesenberg, L. Frenzel, C. Goy, J. Hallmann, Y. Kim, I. Lokteva, V. Markmann, G. Mills, A. Rodriguez-Fernandez, W. Roseker, M. Scholz, R. S. and R. Vagovic, M. Walther, F. Westermeier, A. Madsen, A. Mancuso, G. Grübel, F. Lehmkuhler, Microsecond hydrodynamic interactions in dense colloidal dispersions probed at the european xfel, *IUCrJ* **8**, 775 (2021).
- 510 27. M. Reiser, A. Girelli, A. Ragulskaya, S. Das, S. Berkowicz, M. Bin, M. Ladd-Parada, M. Filianina, H.-F. Poggemann, N. Begam, M. S. Akhundzadeh, S. Timmermann, L. Randolph, Y. Chushkin, T. Seydel, U. Boesenberg, J. Hallmann, J. Möller, A. Rodriguez-Fernandez, R. Rosca, R. Schaffer, M. Scholz, R. Shayduk, A. Zozulya, A. Madsen, F. Schreiber, F. Zhang, F. Perakis, C. Gutt, Resolving molecular diffusion and aggregation of antibody proteins with megahertz x-ray free-electron laser pulses, *Nat. Commun.* **13**, 5528 (2022).
- 515 28. F. Perakis, C. Gutt, Towards molecular movies with x-ray photon correlation spectroscopy, *Phys. Chem. Chem. Phys.* **22**, 19443–19453 (2020).
29. Y. Xu, M. Sikorski, J. Fan, H. Jiang, Z. Liu, Thermal effects of beam profiles on x-ray photon correlation spectroscopy at megahertz x-ray free-electron lasers, *Opt. Express* **30**, 42639–42648 (2022).
- 520 30. O. Bikondoa, On the use of two-time correlation functions for x-ray photon correlation spectroscopy data analysis, *J. Appl. Crystallogr.* **50**, 357–368 (2017).
31. B. Ruta, Y. Chushkin, G. Monaco, L. Cipelletti, E. Pineda, P. Bruna, V. M. Giordano, M. Gonzalez-Silveira, Atomic-scale relaxation dynamics and aging in a metallic glass probed by x-ray photon correlation spectroscopy, *Phys. Rev. Lett.* **109**, 165701 (2012).

- 525 32. F. Dallari, Slow dynamics in colloids and network glasses close to the structural arrest: the stress-relaxation as a root to equilibrium, Ph.D. thesis, University of Trento, department of Physics, via Sommarive 14 (2018).
33. A. Jain, F. Schulz, I. Lokteva, L. Frenzel, G. Grübel, F. Lehmkuhler, Anisotropic and heterogeneous dynamics in an aging colloidal gel, *Soft Matter* **16**, 2864-2872 (2020).
34. K. A. Nugent, Coherent methods in the x-ray sciences, *Adv. Phys.* **59**, 1-99 (2010).
- 530 35. F. Dallari, I. Lokteva, J. Möller, A. Jain, W. Roseker, F. Westermeier, C. Goy, U. Boesenberg, J. Hallmann, A. Rodriguez-Fernandez, M. Scholz, R. Shayduk, A. Madsen, G. Grübel, F. Lehmkuhler, Coherence properties from speckle contrast analysis at the european xfel, *J. Phys. Conf. Ser.* **2380**, 012085 (2022).
36. F. Dallari, M. Reiser, I. Lokteva, A. Jain, J. Möller, M. Scholz, A. Madsen, G. Grübel, 535 F. Perakis, F. Lehmkuhler, Analysis strategies for mhz xpcs at the european xfel, *Appl. Sci.* **11**, 8037 (2021).
37. F. Lehmkuhler, J. Valerio, D. Sheyfer, W. Roseker, M. A. Schroer, B. Fischer, K. Tono, M. Yabashi, T. Ishikawa, G. Grübel, Dynamics of soft nanoparticle suspensions at hard X-ray FEL sources below the radiation-damage threshold, *IUCrJ* **5**, 801–807 (2018).
- 540 38. C. G. Lopez, W. Richtering, Does flory–rehner theory quantitatively describe the swelling of thermoresponsive microgels?, *Soft Matter* **13**, 8271-8280 (2017).
39. Y. Zhang, S. Furry, D. E. Bergbreiter, P. S. Cremer, Specific ion effects on the water solubility of macromolecules: PnIPAM and the hofmeister series, *J. Am. Chem. Soc.* **127**, 14505-14510 (2005). PMID: 16218647.
- 545 40. C. M. Jeffries, M. A. Graewert, D. I. Svergun, C. E. Blanchet, Limiting radiation damage for high-brilliance biological solution scattering: practical experience at the EMBL P12 beamline PETRAIII, *J. Synchrotron Radiat.* **22**, 273–279 (2015).
41. Y. Deng, R. Pelton, Synthesis and solution properties of poly(n-isopropylacrylamide-co-diallyldimethylammonium chloride), *Macromolecules* **28**, 4617-4621 (1995).
- 550 42. Y. Ye, Y. Shangguan, Y. Song, Q. Zheng, Influence of charge density on rheological properties and dehydration dynamics of weakly charged poly(n-isopropylacrylamide) during phase transition, *Polymer* **55**, 2445-2454 (2014).
- 555 43. K. Szczubiałka, R. Loska, M. Nowakowska, Temperature-induced aggregation of the copolymers of n-isopropylacrylamide and sodium 2-acrylamido-2-methyl-1-propanesulphonate in aqueous solutions, *J. Polym. Sci., Part A: Polym. Chem.* **39**, 2784-2792 (2001).

44. B. Berne, R. Pecora, *Dynamic Light Scattering with Applications to Chemistry, Biology and Physics* (Dover, New York, 2000).
45. A. Duri, H. Bissig, V. Trappe, L. Cipelletti, Time-resolved-correlation measurements of temporally heterogeneous dynamics, *Phys. Rev. E* **72**, 051401 (2005).
46. E. Wandersman, A. Duri, A. Robert, E. Dubois, V. Dupuis, R. Perzynski, Probing heterogeneous dynamics of a repulsive colloidal glass by time resolved x-ray correlation spectroscopy, *J. Condens. Matter Phys.* **20**, 155104 (2008).
47. A. Madsen, J. Hallmann, G. Ansaldi, T. Roth, W. Lu, C. Kim, U. Boesenberg, A. Zozulya, J. Möller, R. Shayduk, M. Scholz, A. Bartmann, A. Schmidt, I. Lobato, K. Sukharnikov, M. Reiser, K. Kazarian, I. Petrov, Materials imaging and dynamics (MID) instrument at the european x-ray free-electron laser facility, *J. Synchrotron Radiat.* **28**, 637–649 (2021).

Acknowledgements

We acknowledge European XFEL in Schenefeld, Germany, for provision of X-ray free-electron laser beamtime at MID SASE2 and would like to thank the staff for their assistance.

We acknowledge DESY (Hamburg, Germany), a member of the Helmholtz Association HGF, for the provision of experimental facilities. Parts of this research were carried out at PETRA III and we would like to thank Michael Sprung for assistance in using the beamline P10.

The authors also acknowledge the scientific exchange and support of the Centre for Molecular Water Science (CMWS).

This research was supported in part through the Maxwell computational resources operated at Deutsches Elektronen-Synchrotron DESY, Hamburg, Germany.

Funding:

This work was financially supported by DESY, a member of the Helmholtz Association (HGF), and by the Cluster of Excellence “Advanced Imaging of Matter” of the Deutsche Forschungsgemeinschaft (DFG)—EXC 2056—Project ID No. 390715994.

Data availability:

All data needed to evaluate the conclusions in the paper are present in the paper and/or the Supplementary Materials. Data recorded for the experiment at the European XFEL are available at doi:10.22003/XFEL.EU-DATA-002616-00.

Author contribution: F.D., F.L. and G.G. conceived the idea. I.L. synthesized and prepared the samples. C.G. performed the DLS experiments. J.M., U.B., J.H., A.R.-F., M.S., R.S., and A.M. prepared the experimental setup at European XFEL and operated the MID instrument. J.M., U.B., J.H., A.R.-F., M.S., R.S., I.L., and F.L. performed the experiment. F.D., J.M., W.R., C.G., F.W. performed the online data analysis. F.D. analyzed the data. F.D. and F.L. interpreted and modeled the data. F.D. wrote the manuscript with input from all authors.